

# ANTIFUNGAL ASSESSMENT REPORT

REPORT NO.: 2427511.A

DATE: January 05, 2009

A.A.T.C.C. TEST METHOD 30 - 2004 - *Aspergillus niger* (ATCC #6275)

TO: Alain Vezina  
Absoluson  
694 St. Vallier Ouest  
Quebec City, Quebec  
Canada, G1N 1C8

FOR:

C: Bob Beauchemin

SAMPLE(S) DESCRIPTION: One wood fibre panel, treated with Ultra-Fresh DM-50N, was received for assessment of antimicrobial activity.

\* The width of the growth-free zone surrounding the test specimen.

\*\* Percentage of specimen free of growth.

## TEST RESULTS:


SAMPLE DESCRIPTION	GROWTH-FREE ZONE (MM)*	SURFACE INHIBITION (%)**
1. Sound Barrier Wood Fibre Panel Treated with 10 g/L Ultra-Fresh DM-50N with Brown Pigment	>15	100

Note: The level of treatment stated above indicates theoretical levels only.

COMMENTS: The samples demonstrated good activity against the *A. niger* test organism.



Chris Liu, M.A.Sc.  
Microbiologist



Justin Williams, B.Sc.  
Microbiologist

**THOMSON RESEARCH ASSOCIATES INC.**

49 Gervais Drive, Toronto, Ontario, Canada, M3C 1Y9 Tel: (416) 955-1881 Fax: (416) 955-1887